

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 7608 (1987): Phosphor bronze wire for general engineering purposes [MTD 8: Copper and Copper Alloys]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 7608 - 1987
(Reaffirmed 2006)

Indian Standard

**SPECIFICATION FOR
PHOSPHOR BRONZE WIRES FOR
GENERAL ENGINEERING PURPOSES**

(First Revision)

Third Reprint JULY 2007
(Including Amendment No. 1)

UDC 669.35.779.426

© Copyright 1988

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

AMENDMENT NO. 1 JUNE 2004
TO
IS 7608 : 1987 SPECIFICATION FOR
PHOSPHOR BRONZE WIRES FOR GENERAL
ENGINEERING PURPOSES

(First Revision)

(Page 4, clause 3.1, line 2) — Substitute 'IS 1387 : 1993‡' for 'IS : 1387 - 1967‡'.

(Page 4, footnote marked '‡') — Substitute the following for the existing footnote:

‘‡General requirements for the supply of metallurgical materials (*second revision*).’

(Page 5, clause 7.1, line 2) — Substitute 'IS 1608 : 1995†' for 'IS : 2656 - 1964†'.

(Page 5, footnote marked '†') — Substitute the following for the existing footnote:

‘†Mechanical testing of metals — Tensile testing (*second revision*).’

(MTD 8)

Indian Standard

SPECIFICATION FOR PHOSPHOR BRONZE WIRES FOR GENERAL ENGINEERING PURPOSES

(*First Revision*)

Copper and Copper Alloys Sectional Committee, SMDC 11

Chairman

DR L. R. VAIDYANATH

Representing

Indian Copper Development Centre, Calcutta

Members

SHRI D. DE SARKAR (<i>Alternate</i> to DR L. R. Vaidyanath)	
ADDITIONAL DIRECTOR (MET), M & C DIRECTORATE, RDSO, LUCKNOW	Ministry of Railways
SHRI DEV KUMAR AGGARWAL	Bralco Metal Industries Pvt Ltd, Bombay
SHRI RAJ KUMAR AGGARWAL (<i>Alternate</i>)	
SHRI R. T. BAJAJ	Kumani Tubes Ltd, Bombay
SHRI K. L. BARUI	National Test House, Calcutta
SHRI H. P. DUBEY (<i>Alternate</i>)	
SHRI J. NAGESH BHATT	Indian Telephone Industries Ltd, Bangalore
SHRI A. R. SUKUMARAN (<i>Alternate</i>)	
SHRI C. D. BHATTACHARYA	Hindustan Cables Ltd, Burdwan
SHRI M. JHA (<i>Alternate</i>)	
SHRI BALKRISHNA BINANI	Rashtriya Metal Industries Ltd, Bombay
DR V. S. PATKAR (<i>Alternate</i>)	
PROF A. D. BOHRA	Alcobex Metal (P) Ltd, Jodhpur
SHRI KULDEEP DHINGRA (<i>Alternate</i>)	
SHRI M. K. CHOUDHURY	Bengal Ingot Co Ltd, Calcutta
SHRI P. R. DHAR	Indian Standard Metal Co Ltd, Bombay
SHRI N. R. MANIAR (<i>Alternate</i>)	
SHRI B. DUTTA	Directorate General of Ordnance Factories, Calcutta
SHRI S. K. GHOSH (<i>Alternate</i>)	
SHRI A. V. HARNE	Bharat Heavy Electricals Ltd
SHRI P. V. DIXIT (<i>Alternate I</i>)	
SHRI M. N. CHANDRASEKHARIAH (<i>Alternate II</i>)	
SHRI D. P. JAIN	Saru Smelting Pvt Ltd, Meerut
SHRI DAVINDER KUMAR JAIN	Aggarwal Metal Works Pvt Ltd, Rewari
SHRI RAJIV JAIN (<i>Alternate</i>)	

(*Continued on page 2*)

© Copyright 1988

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 7608 - 1987

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI R. P. KESAN	KMA Ltd, Bombay
SHRI A. H. SABHACHANDANI (<i>Alternate</i>)	
SHRI S. K. KHANDEKAR	Vanaz Engineers (Pvt) Ltd, Pune
SHRI P. K. D. LEE	Ministry of Finance
SHRI S. BAGCHI (<i>Alternate</i>)	
SHRI R. C. MATHUR	Ministry of Defence (DGI)
SHRI N. L. VAIDYA (<i>Alternate</i>)	
SHRI A. K. MITRA	Neo Pipes and Tubes Co Ltd, Calcutta
DR P. R. MUKHERJEE	Incab Industries Ltd, Jamshedpur
SHRI TRILOK SINGH (<i>Alternate</i>)	
SHRI G. R. K. MURTHY	Ministry of Defence (R & D)
SHRI I. N. BHATIA (<i>Alternate</i>)	
SHRI S. K. PANDEY	Directorate General of Supplies and Disposals, New Delhi
SHRI H. S. RAMACHANDRA	Hindustan Machines Tools Ltd, Bangalore
SHRI A. SHANTHARAM (<i>Alternate I</i>)	
SHRI V. N. VENKATESAN (<i>Alternate II</i>)	
SHRI T. RAMASUBRAMANIAN	Directorate General of Technical Development, New Delhi
SHRI T. R. MOHAN RAO (<i>Alternate</i>)	
SHRI P. S. RAMASWAMY	Bhandary Metallurgical Corporation Ltd, Bombay
SHRI M. K. RAO	Indian Non-Ferrous Metals Manufacturer's Association, Bombay
SHRI P. B. RAO	Directorate of Warships Projects (Navy), New Delhi
SHRI K. R. NAIR (<i>Alternate</i>)	
SHRI D. K. SEHGAL	Leader Engineering Works, Jalandhar
DR P. D. SHARMA	Hindustan Copper Ltd, Calcutta
SHRI S. C. SIVARAMKRISHNAN	National Metallurgical Laboratory (CSIR), Jamshedpur
SHRI J. SRIDHARAN	Ministry of Steel and Mines
SHRI P. SRIRAM	Rapsri Engineering Industries Pvt Ltd, Bangalore
SHRI N. S. SURANA	Multimetals Ltd, Kota
SHRI N. G. RAMAKRISHNAN (<i>Alternate</i>)	
SHRI S. S. VAIDYANATHAN	J. B. Metal Industries Ltd, Bombay
SHRI HASMUKH J. GOR (<i>Alternate</i>)	
SHRI Y. P. VIJ	Minerals and Metals Trading Corporation of India Ltd, New Delhi
SHRI K. DHAKSHINAMURTHY (<i>Alternate</i>)	
SHRI B. MUKHERJI, Director (Struc and Met)	Director General, BIS (<i>Ex-officio Member</i>)

Secretary

SHRI JAGMOHAN SINGH
Deputy Director (Metals), BIS

Indian Standard

SPECIFICATION FOR PHOSPHOR BRONZE WIRES FOR GENERAL ENGINEERING PURPOSES

(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards on 25 June 1987, after the draft finalized by the Copper and Copper Alloys Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 This standard was first published in 1975. In this revision, the following modifications have been made:

- a) Definition of wire has been brought in line with IS : 3288- (Part 3)-1986* to which reference has also been made in this standard;
- b) Clauses for method for chemical analysis, and dimensions and tolerances have been revised and latest reference have been made;
- c) Tables on chemical composition and physical properties have been modified; and
- d) Sampling and criteria for conformity have been modified.

0.3 Phosphor bronze wires are used for many applications specially for springs, in different conditions of tension depending on the applicability. The chemical composition and mechanical properties embrace various applications of wire for general engineering purposes including filler metal.

0.3.1 Requirements for phosphor bronze wires used for fourdrinier cloth are covered in IS : 10710-1983†.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in

*Glossary of terms relating to copper and copper alloys: Part 3 Wrought forms.

†Specification for phosphor bronze wires for fourdrinier cloth.

IS : 7608 - 1987

accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard covers requirements for two grades of phosphor bronze wires used for general engineering purposes.

2. TERMINOLOGY

2.0 For the purpose of this standard, the following definition as given in IS : 3288 (Part 3)-1986† shall apply.

2.1 Wire — A solid section of uniform cross-section along its whole length and the distance between two parallel faces not exceeding 6 mm may be supplied in straight length or in coil or in spools.

3. SUPPLY OF MATERIAL

3.1 General requirements relating to the supply of material shall conform to IS : 1387-1967‡.

4. FREEDOM FROM DEFECTS

4.1 The material shall be clean, smooth and free from harmful defects. There shall be no joints in the wire except those made in the rod or wire before final drawing.

5. CONDITION

5.1 The material shall be supplied in one of the following conditions as specified by the purchaser:

- a) Annealed (soft) (O),
- b) Half hard (HB),
- c) Hard (HD), and
- d) Extra hard (HE).

*Rules for rounding off numerical values (*revised*).

†Glossary of terms relating to copper and copper alloys: Part 3 Wrought forms.

‡General requirement for the supply of metallurgical materials (*first revision*).

6. CHEMICAL COMPOSITION

6.1 The material shall have the chemical composition as given in Table 1.

TABLE 1 CHEMICAL COMPOSITION OF PHOSPHOR BRONZE WIRES

GRADE	PERCENT				
	Tin	Phosphorous	Lead	Total Impurities	Copper
I	4.2-5.5	0.02-0.40	Max	Max	Remainder
II	5.5-7.5	0.02-0.40	0.05	0.20	Remainder

6.2 The chemical composition shall be determined either by the methods specified in IS : 4027-1967* or its relevant parts or any other established instrumental/chemical method. In case of dispute, the procedure specified in IS : 4027-1967* or its relevant parts shall be the referee method.

7. MECHANICAL PROPERTIES

7.1 Tensile Test — The material, when tested in accordance with IS : 2656-1964†, shall have the properties as given in Table 2.

TABLE 2 MECHANICAL PROPERTIES OF PHOSPHOR BRONZE WIRES

GRADE	CONDITION	DIAMETER		TENSILE STRENGTH MPa		ELONGATION PERCENT ON GAUGE
		Over	Up to and Including	Min	Max	LENGTH OF 100 mm, Min
		mm	mm			
I	O	0.45	6.0	340	—	40
	HB	0.45	6.0	540	700	—
	HD	0.45	6.0	700	850	—
	HE	0.45	2.5	850	—	—
		2.5	6.0	800	—	—
II	O	0.45	6.0	370	—	50
	HB	0.45	6.0	590	740	—
	HD	0.45	6.0	740	900	—
	HE	0.45	2.5	900*	—	—
		2.5	6.0	850	—	—

*For special requirements, the purchaser may specify a minimum of 925 MPa for wires of 0.45 to 0.50 mm diameter.

NOTE — 1 N/mm² = 0.102 kgf/mm² = 1 MPa.

*Method of chemical analysis of bronzes.

†Method for tensile testing of copper and copper alloy wires.

7.2 Wrapping Test — The wire in the hard and extra hard condition shall be wrapped around a wire of its own diameter to form a close helix of eight turns. This shall then be unwrapped for six turns. The wire shall not break or show any cracks when subjected to this test. For details, see also IS : 1755-1983*.

8. DIMENSIONS AND TOLERANCES

8.1 Dimension — The diameter of the wire shall be as required by the purchaser and stated in the order.

8.2 Tolerances — The tolerance on the diameter shall be in accordance with IS : 9861-1981†.

8.2.1 Where tolerances other than these are required, these shall be subject to agreement between the purchaser and the supplier.

8.3 Measurement — The diameter of round wire shall be determined by means of a suitable micrometer and by taking the mean of the two measurements at right angles made at the same cross-section of the sample.

9. SAMPLING AND CRITERIA FOR CONFORMITY

9.0 Unless otherwise agreed to between the purchaser and the supplier, the following sampling procedure and criteria for conformity shall hold good.

9.1 Lot — In any consignment, all the coils of wire of the same size, grade and temper manufactured under similar conditions of production shall be grouped together to constitute a lot. However, a lot shall not exceed 1 000 kg in mass. If necessary, two or more lots shall be formed on the basis of the mass of the consignment.

9.2 Each coil of wire shall be examined from the lot for freedom from defects and for tolerance on diameters. Any coil found defective shall be rejected.

9.3 For chemical composition, one test shall be conducted for each 200 kg of wire or part thereof in the lot. For this purpose, necessary number of coil shall be selected at random in accordance with IS : 1817-1961‡.

*Method for wrapping test of metallic wire (*first revision*).

†Dimensions for wrought copper and copper alloy wires for general engineering purposes.

‡Methods of sampling non-ferrous metals for chemical analysis.

9.3.1 If the results of chemical analysis as obtained for each of the constituent satisfy the corresponding requirements, the lot shall be considered as conforming to the chemical requirements of the specification.

9.4 The number of samples for mechanical tests (tensile test, wrapping test) shall be at the rate of one per every 100 kg of wire or part thereof in the lot.

9.4.1 The lot shall be considered as conforming to the requirements of the mechanical tests, if all the test results on different samples satisfy the corresponding requirements.

10. RETESTS

10.1 If a test result of chemical analysis fails to satisfy the requirements for any of the constituents, two more tests for that constituent shall be done on the same sample in order to confirm that the analysis has been done properly. If both the test results satisfy the relevant requirements, the lot shall be considered as conforming to the specification, otherwise not.

10.2 If any one of the test pieces first selected fails to pass the tensile test and wrapping test, two further samples from the same lot shall be selected for testing, one of which shall be from the coil from which the original test sample was taken, unless that coil has been withdrawn by the supplier.

10.2.1 If the test pieces from both these additional samples pass, the lot represented by the test sample shall be deemed to comply with this standard. If the test pieces from either of these additional samples fail, the lot represented by the test samples shall be rejected.

11. PACKING

11.1 The wires shall be coiled carefully and each length of wire shall be made up into a separate coil weighing up to 50 kg.

11.2 The inner diameter of coil depending on size of the wire shall be subject to agreement between the purchaser and the supplier.

11.3 The coils shall be suitably packed to avoid damage during transit.

12. MARKING

12.1 Suitable tags with marking made on them to show the size, grade, temper, lot number, data of manufacture, mass of the material, in addition to name of the manufacturer and any such information required by the purchaser, shall be attached to each coil of the material.

12.1.1 The coils of wire may also be marked with the Standard Mark.

NOTE — The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

13. TEST CERTIFICATE

13.1 The supplier shall provide test certificate for each consignment giving information like lot number, corresponding chemical composition and mechanical test results.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 23230131, 23233375, 23239402

Fax: 91+011 23239399, 23239382

E-Mail : info@bis.org.in

website : <http://www.bis.org.in>

Central Laboratory:

Plot No. 20/9, Site IV, Sahibabad Industrial Area, SAHIBABAD 201010

Telephone

277 0032

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

2323 7617

*Eastern : 1/14 CIT Scheme VII M, V.I.P. Road, Kankurgachi, KOLKATA 700054

2337 8662

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

260 9285

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

2254 1984

†Western: Manakalaya, E9, MIDC, Behind Marol Telephone Exchange,
Andheri (East), MUMBAI 400093

2832 9295

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001

560 1348

Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE

839 4955

Commercial-cum-Office Complex, Opp. Dushera Maidan, Arera Colony,
Bittan Market, BHOPAL 462016

242 3452

62-63, Ganga Nagar, Unit VI, BHUBANESHWAR 751001

240 3139

5th Floor, Kovai Towers, 44 Bala Sundaram Road, COIMBATORE 641018

221 0141

SCO 21, Sector 12, Faridabad 121007

229 2175

Savitri Complex, 116 G.T. Road, GHAZIABAD 201001

286 1498

53/5 Ward No. 29, R.G. Barua Road, 5th By-lane, Apurba Sinha Path,
GUWAHATI 781003

245 6508

5-8-56C, L.N. Gupta Marg, Nampally Station Road, HYDERABAD 500001

2320 1084

Prithavi Raj Road, Opposite Bharat Overseas Bank, C-Scheme, JAIPUR 302001

222 3282

11/418 B, Sarvodaya Nagar, KANPUR 208005

223 3012

Sethi Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road,
LUCKNOW 226001

261 8923

H. No. 15, Sector-3, PARWANOO, Distt. Solan (H.P.) 173220

235 436

Plot No A-20-21, Institutional Area, Sector 62, Goutam Budh Nagar, NOIDA 201307

240 2206

Pattiputra Industrial Estate, PATNA 800013

226 2808

Plot Nos. 657-660, Market Yard, Gultkdi, PUNE 411037

2427 4804

"Sahajanand House" 3rd Floor, Bhaktinagar Circle, 80 Feet Road,
RAJKOT 360002

237 8251

T.C. No. 2/275 (1 & 2), Near Food Corporation of India, Kesavadasapuram-Ulloor Road,
Kesavadasapuram, THIRUVANANTHAPURAM 695004

255 7914

1st Floor, Udyog Bhavan, VUDA, Siripuram Junction, VISHAKHAPATNAM-03

271 2833

*Sales Office is at 5 Chowringhee Approach, P.O. Princep Street, KOLKATA 700072

2355 3243

†Sales Office (WRO) Plot No. E-9, MIDC, Rd No. 8, Behind Telephone Exchange,
Andheri (East), Mumbai-400 0093

2832 9295